

Concerns : Raw Material

**Control Sheet N° : FCM\_2024-0592**

Starting date : 25/11/2024 End date : 03/12/2024


**Product Characteristics**


<b>Supplier:</b>	1265
<b>Raw Material:</b>	Alligator mat champagne
<b>Finishing:</b>	<b>SAFARI</b> <b>ALLIGATOR</b>
<b>Material reference:</b>	A-RM-01422
<b>Material lot :</b>	B-CM- 0028141

**Summary of results**

<input checked="" type="checkbox"/> Adhesive Tape				OK
<input checked="" type="checkbox"/> Folding				OK
<input checked="" type="checkbox"/> Rubbing test on moist state (Veslic)	50 & 100 cycles	5/5		5/5
<input checked="" type="checkbox"/> Colour change	Aspect	5/5		5/5
<input checked="" type="checkbox"/> Rubbing test on dry state (Veslic)	50 & 100 cycles	5/5		5/5
<input checked="" type="checkbox"/> Colour change	Aspect	5/5		5/5
<input checked="" type="checkbox"/> Colour fastness to perspiration				5/5
<input checked="" type="checkbox"/> Colour fastness to artificial light				4/5
<input type="checkbox"/> Rubbing test on moist state (artificial sweat, Veslic)	50 & 100 cycles			
<input type="checkbox"/> Colour change	Aspect			

**Comments**

Adhesive tape, 3M810	Observations
	Exfoliation OK
	No visible alteration

Folding twice	Observations
	Change OK
	Aesthetic and visual alteration with formation of slight wrinkles.

# TEST REPORT


Control Sheet N° :	FCM_2024-0592
--------------------	---------------

**Rubbing test on moist state (Veslic), partial extension**




Observations		
Felt staining	Final colour change	Aspect
50 Cycles	5/5	5/5
5/5	No staining of the colour on the felts. No change of the colour at 150 cycles.	
100 Cycles		
5/5		

**Rubbing test on dry state (Veslic), partial extension**



Observations		
Felt staining	Final colour change	Aspect
50 Cycles	5/5	5/5
5/5	No staining of the colour on the felts. No change of the colour at 150 cycles.	
100 Cycles		
5/5		

**Colour fastness to perspiration, 72 hours, ambient temperature, artificial sweat according to ISO 3160-2**



Observations
Staining on blotting paper
5/5
No staining of the colour on the blotting paper from the surface.

**Rubbing test on moist state (Artificial sweat ISO 3160-2, Veslic), partial extension**



Felt staining	Final colour change	Aspect
50 Cycles		
100 Cycles		

**Colour fastness to artificial light, approx. 7,8 MJ/m²**



Observations
Colour change
4/5
Slight change of the colour on the exposed area.

