

TEST REPORT

Concerns : Raw Material

Control Sheet N° : FCM_2026-0139

Starting date : 05/03/2026 End date : 28/03/2026

Product Characteristics

Supplier:	237
Raw Material:	Alligator sia ric bleu marine
Finishing:	HIGH SHINY ALLIGATOR
Material reference:	A-RM-02395
Material lot :	A-CM- 0043614

Summary of results

<input checked="" type="checkbox"/> Adhesive Tape	Exfoliation	OK	
<input checked="" type="checkbox"/> Folding	Change	OK	
<input checked="" type="checkbox"/> Rubbing test on moist state (Veslic)	50 & 100 cycles	5/5	5/5
	Colour change & aspect	5/5	5/5
<input checked="" type="checkbox"/> Rubbing test on dry state (Veslic)	50 & 100 cycles	5/5	5/5
	Colour change & aspect	5/5	5/5
<input checked="" type="checkbox"/> Colour fastness to perspiration	Moist & dry staining	4/5	4,5/5
<input checked="" type="checkbox"/> Colour fastness to artificial light	Colour change	3,5/5	
<input type="checkbox"/> Rubbing test on dry state (artificial sweat, Veslic)	50 & 100 cycles		
	Colour change & aspect		

Comments

Adhesive tape, 3M810 **Observations**



Exfoliation	OK
--------------------	----

No visible alteration

Folding twice **Observations**



Change	OK
---------------	----



Aesthetic and visual alteration with formation of slight wrinkles.

TEST REPORT

Control Sheet N° :	FCM_2026-0139
--------------------	---------------

Rubbing test on moist state (Veslic), partial extension



Observations



Felt staining	Final colour change	Aspect
50 Cycles	5/5	5/5
5/5	No staining of the colour on the felts. No change of the colour at 150 cycles.	
100 Cycles		
5/5		

Rubbing test on dry state (Veslic), partial extension


Observations



Felt staining	Final colour change	Aspect
50 Cycles	5/5	5/5
5/5	No staining of the colour on the felts. No change of the colour at 150 cycles.	
100 Cycles		
5/5		

Colour fastness to perspiration, 72 hours, ambient temperature, artificial sweat according to ISO 3160-2

Observations



Staining on blotting paper	
Moist state	Dry state
4/5	4,5/5

On dry state, very slight staining of the colour on the blotting paper from the surface, intense staining on the blotting paper from cutting edges. No change of the colour on the tested sample, cotation 5.

Rubbing test on moist state (Artificial sweat ISO 3160-2, Veslic), partial extension


Observations



Felt staining	Final colour change	Aspect
50 Cycles		
100 Cycles		

Colour fastness to artificial light, approx. 7,8 MJ/m², xenon lamp

Observations



Colour change
3,5/5

Slight to moderate change of the colour on the exposed area.

