

TEST REPORT

Concerns : Raw Material

Control Sheet N° : FCM_2026-0047

Starting date : 27/01/2026 End date : 19/02/2026

Product Characteristics


Supplier:	237
Raw Material:	Alligator semi-mat ric bleu
Finishing:	SAFARI ALLIGATOR
Material reference:	A-RM-02407
Material lot :	A-CM- 0039053

Summary of results

<input checked="" type="checkbox"/> Adhesive Tape	Exfoliation	OK	
<input checked="" type="checkbox"/> Folding	Change	OK	
<input checked="" type="checkbox"/> Rubbing test on moist state (Veslic)	50 & 100 cycles	4,5/5	4,5/5
	Colour change & aspect	5/5	5/5
<input checked="" type="checkbox"/> Rubbing test on dry state (Veslic)	50 & 100 cycles	4,5/5	5/5
	Colour change & aspect	5/5	5/5
<input checked="" type="checkbox"/> Colour fastness to perspiration	Moist & dry staining	4/5	5/5
<input checked="" type="checkbox"/> Colour fastness to artificial light	Colour change	3,5/5	
<input type="checkbox"/> Rubbing test on dry state (artificial sweat, Veslic)	50 & 100 cycles		
	Colour change & aspect		

Comments

Adhesive tape, 3M810	Observations	
	Exfoliation	OK
	No visible alteration	

Folding twice	Observations	
	Change	OK
	No visible alteration.	

TEST REPORT



Control Sheet N° :	FCM_2026-0047
--------------------	---------------

Rubbing test on moist state (Veslic), partial extension




Observations		
Felt staining	Final colour change	Aspect
50 Cycles	5/5	5/5
4,5/5	Very slight staining of the colour on the felts. No change of the colour at 150 cycles.	
100 Cycles		
4,5/5		

Rubbing test on dry state (Veslic), partial extension



Observations		
Felt staining	Final colour change	Aspect
50 Cycles	5/5	5/5
4,5/5	Very slight staining of the colour on the first felt, no staining on the second. No change of the colour at 150 cycles.	
100 Cycles		
5/5		

Colour fastness to perspiration, 72 hours, ambient temperature, artificial sweat according to ISO 3160-2




Observations		
Staining on blotting paper		
Moist state	Dry state	
4/5	5/5	
On dry state, no staining staining of the colour on the blotting paper from the surface, slight staining on the blotting paper from cutting edges. No change of the colour on the tested sample, cotation 5.		

Rubbing test on moist state (Artificial sweat ISO 3160-2, Veslic), partial extension



Observations		
Felt staining	Final colour change	Aspect
50 Cycles		
100 Cycles		

Colour fastness to artificial light, approx. 7,8 MJ/m², xenon lamp



Observations	
Colour change	
3,5/5	Slight to moderate change of the colour on the exposed area.

