

BRASPORT

SWITZERLAND – SINCE 1946

TEST REPORT

Concerns : Raw Material

Control Sheet N° :

FCM_2025-0138

Starting date :

10/03/2025

End date :

28/03/2025

Product Characteristics

Supplier:	1265
Raw Material:	Alligator glossy rouge carmin
Finishing:	High shiny ALLIGATOR
Material reference:	A-RM-02441
Material lot :	A-CM- 0041620

Summary of results

<input checked="" type="checkbox"/> Adhesive Tape			OK
<input checked="" type="checkbox"/> Folding			OK
<input checked="" type="checkbox"/> Rubbing test on moist state (Veslic)	50 & 100 cycles	3/5	1,5/5
<input checked="" type="checkbox"/> Colour change	Aspect	2,5/5	2/5
<input checked="" type="checkbox"/> Rubbing test on dry state (Veslic)	50 & 100 cycles	5/5	5/5
<input checked="" type="checkbox"/> Colour change	Aspect	5/5	5/5
<input checked="" type="checkbox"/> Colour fastness to perspiration			5/5
<input checked="" type="checkbox"/> Colour fastness to artificial light			4/5
<input type="checkbox"/> Rubbing test on moist state (artificial sweat, Veslic)	50 & 100 cycles		
<input type="checkbox"/> Colour change	Aspect		

Comments

Adhesive tape, 3M810



Observations

Exfoliation

OK

No visible alteration

Folding twice



Observations

Change

OK

Aesthetic and visual alteration with formation of slight wrinkles.

BRASPORT

SWITZERLAND – SINCE 1946

TEST REPORT

Control Sheet N° :

FCM_2025-0138

Rubbing test on moist state (Veslic), partial extension



50 cycles



100 cycles



Observations

Felt staining

Final colour change

Aspect

50 Cycles

2,5/5

2/5

3/5

100 Cycles

1,5/5

Heterogeneous and moderate staining of the colour with particles on the first felt, significant to intense with particles on the second. Moderate to significant change of the colour at 150 cycles, whitened depending on the orientation, swollen, exfoliated on top of scales, cotation 1,5.

Rubbing test on dry state (Veslic), partial extension



50 cycles



100 cycles



Observations

Felt staining

Final colour change

Aspect

50 Cycles

5/5

5/5

5/5

100 Cycles

5/5

No staining of the colour on the felts. No change of the colour at 150 cycles.

Colour fastness to perspiration, 72 hours, ambient temperature, artificial sweat according to ISO 3160-2



Observations

Staining on blotting paper

5/5

No staining of the colour on the blotting paper from the surface. Moderate to significant and point staining of the colour on the blotting paper from cutting edges, cotation 2,5/5. Moderate change of the colour on the tested sample, cotation 3, clearer with decrease of the brightness, increase of the relief.

Rubbing test on moist state (Artificial sweat ISO 3160-2, Veslic), partial extension

50 cycles

100 cycles

Felt staining


Final colour change

Aspect

50 Cycles

100 Cycles

Colour fastness to artificial light, approx. 7,8 MJ/m², metal halide lamp



Observations

Colour change

4/5

Slight change of the colour on the exposed area.

TEST REPORT

Control Sheet N° : FCM_2025-0138

Starting date : 10/03/2025

Chromium VI test	Observations
	Upper limit < 3 ppm
pH test	
	Value

Standards references

Adhesive Tape	Designation
INS-23-239-D-F / SWATCH GROUP ISO 2419, Physical and mechanicals trials -Preparation and sample conditioning	OK No visible alteration
	OK Slight and sparce exfoliation visible on tape, nothing visible on material.
	KO Slight finishing removal, visible on tape and material. Evident exfoliation and removal of numerous finishing particules on tape and material. Finishing and underlying material removal.
Folding	Designation
Inhouse Method ISO 2419, Physical and mechanicals trials -Preparation and sample conditioning	OK No visible alteration.
	OK Aesthetic and visual alteration with formation of slight wrinkles.
	To assess by the customer Aesthetic and visual alteration of color with formation of slight wrinkles.
	KO Formation of wrinkles and cracks of the finishing.
	KO Formation of wrinkles and finishing peeling off.
KO Exfoliation of finishing with tearing of underlying material.	

Rubbing tests (moist, dry, artificial sweat, veslic)

Colour fastness to perspiration

INS-23-229-C-f / SWATCH GROUP
 ISO 2419, Preparation and sample conditioning
 ISO 11640, Colour fastness to cycles of to-and-fro rubbing
ISO 105-A02, Greyscale for assessing change in colour
ISO 105-A03, Greyscale for assessing staining

INS-23-221-D-f / SWATCH GROUP
 NIHS 96-50, Chemical and climatic resistance of a watch case
 ISO 2419, Preparation and sample conditioning
ISO 105-A03, Greyscale for assessing staining

Colour fastness to artificial light

Cosmetic Products Resistance

INS-23-230-C-F / SWATCH GROUP
 ISO 2419, Preparation and sample conditioning
 NIHS 96-50, Chemical and climatic resistance of a watch case
ISO 105-A02, Greyscale for assessing change in colour

INS-23-241-B-F / SWATCH GROUP
ISO 105-A03, Greyscale for assessing staining
NIHS 96-50, Chemical and climatic resistance of a watch case
Solutions used:
 Waterproof NIVEA SUN SPRAY, factor 20
 Hugo Boss perfume, HUGO
 Anti Brumm Forte insect repellent, containing N,N-diethyl-m-toluamide
 (No CAS : 134-62-3)

Carried out by : Isabelle Brun

Modified by :

Date: