

Concerns : Raw Material

Control Sheet N° :

FCM_2024-0555

Starting date : 05/11/2024 End date : 14/11/2024

Product Characteristics

Supplier:	379		
Raw Material:	Alligator noble gris		
Finishing:	NOBLE	ALLIGATOR	
Material reference:	A-RM-03108		
Material lot :	B-CM- 0028059		

Summary of results

<input checked="" type="checkbox"/> Adhesive Tape				KO
<input checked="" type="checkbox"/> Folding				#N/D
<input checked="" type="checkbox"/> Rubbing test on moist state (Veslic)	50 & 100 cycles	2/5		1,5/5
<input checked="" type="checkbox"/> Colour change	Aspect	4/5		3/5
<input checked="" type="checkbox"/> Rubbing test on dry state (Veslic)	50 & 100 cycles	4/5		4/5
<input checked="" type="checkbox"/> Colour change	Aspect	3,5/5		3/5
<input checked="" type="checkbox"/> Colour fastness to perspiration				2/5
<input checked="" type="checkbox"/> Colour fastness to artificial light				5/5
<input type="checkbox"/> Rubbing test on moist state (artificial sweat, Veslic)	50 & 100 cycles			
<input type="checkbox"/> Colour change	Aspect			

Comments

Observed stainings and changes are inherent to the finishing of the tested material.

Adhesive tape, 3M810

Observations



Exfoliation

KO

Slight finishing removal, visible on tape and material.

Folding twice

Observations



Change


#N/D

TEST REPORT

Control Sheet N° :

FCM_2024-0555

Rubbing test on moist state (Veslic), 500 grams



50 cycles



100 cycles



Observations

Felt staining

Final colour change

Aspect

50 Cycles

4/5

3/5

2/5

100 Cycles

1,5/5

Significant staining of the colour on the first felt, intense to significant staining of the colour on the second felt. Slight change of the colour at 150 cycles, with slight wear. Water mark with hardness.

Rubbing test on dry state (Veslic), 500 grams



50 cycles



100 cycles



Observations

Felt staining

Final colour change

Aspect

50 Cycles

3,5/5

3/5

4/5

100 Cycles

4/5

Slight staining of the colour on the felts. Moderate to slight change of the colour at 150 cycles, with shiny aspect.

Colour fastness to perspiration, 72 hours, ambient temperature, artificial sweat according to ISO 3160-2



Observations

Staining on blotting paper

2/5

Significant staining of the colour on the blotting paper from the surface.

Rubbing test on moist state (Artificial sweat ISO 3160-2, Veslic), 500 grams

50 cycles

100 cycles

Felt staining

Final colour change

Aspect

50 Cycles

100 Cycles

Observations

Colour change

5/5

No change of the colour on the exposed area.

Colour fastness to artificial light, approx. 7,8 MJ/m²



